

PORTABLE DIGITAL HARDNESS TESTER

MATERIAL	HLD	HV	HB	HRC	HRB	HS	TENSILE STRENGTH (MPa)
Steel & Cast Steel	300-900	81-955	81-654	20-68	38-100	32-100	375-2639
Tool Steel	300-840	80-898		20-67			
Stainless Steel	300-800	85-802	85-655		46-101		
Cast Iron	360-650		93-334				
Cast Aluminium Alloy	170-570		19-164		23-84		
Brass	200-550		40-173		13-95		
Bronze	300-700		60-290				
Copper	200-690		45-315				